



2024
EDITION

CAR REFINISHING

HIGH- QUALITY RESINS FOR RELIABLE COATING SOLUTIONS.

THE SECRET INSIDE EXCELLENT PRODUCTS

CAR REFINISHING

EXCELLENT MECHANICAL PROPERTIES, SUPERIOR OUTDOOR DURABILITY, AND OUTSTANDING APPEARANCE ARE GUARANTEED.

GOLDEN RESINS

We produce around 70,000 tons of liquid resins annually, including coating and composite resins. Our coating resin brands – DOMACRYL, DOMOPOL, DOMALKYD, DOMEMUL, DOMOPUR and ATRESIN – have achieved a strong market position and are trusted for their quality and performance. With the combined strength of two strong production companies, ATCOAT and Helios Resins, we serve more than 50 countries worldwide. Our production sites in Germany and Slovenia allow us to deliver our quality resins throughout Europe and beyond. A broad product portfolio, intensive R&D and innovation capabilities, high production flexibility, and superior customer service are the strengths of Helios Resins and ATCOAT as a joint specialist for synthetic resins.

SUSTAINABLE APPROACH

By developing advanced, green, and long-lasting materials, we reduce emissions of hazardous organic solvents, incorporate bio-renewable raw materials and create a potential for energy savings. Our sustainable approach encompasses the production of bio-based materials, water-based resins, high solids, BPA non-intent resins, recycling, and participation in EU initiatives. We are the first in Slovenia to be ISCC Plus certified and offer several products made from sustainable raw materials that are certified in all parts of the value chain back to the point of origin. A sustainable future matters greatly to us, our business, and our customers. We are proud to see this reflected in the EcoVadis Gold Medal we received for our sustainability performance.

DEVELOPED WITH ADVANCED TECHNOLOGIES

Our laboratories and production facilities are fully equipped with the most advanced technologies, which enables the development and production of even the most complex solvent and waterborne resins. Our R&D has advanced skills as well as equipment for polyester and acrylic chemistry, including synthesis under pressure. By continually upgrading our production lines and expanding our production capacities, we can meet the most rigorous and complex needs and demands of our customers.

QUALITY OF SERVICE

We are committed to providing a flexible and reliable service while satisfying our customers' specific requests. Helios Resins and ATCOAT ensure the quality, stability and reproducibility of every delivery. Our extensive know-how, resulting from more than 100 years of experience, enables us to provide solutions to our customers' challenges. We produce tailor-made resins for specific needs and offer support in developing customized applications.

ACRYLIC SOLVENTBORNE 2K RESINS

RESIN	DELIVERY FORM	ACID VALUE on solid resin [mg KOH/g]	HYDROXYL VALUE on solid resin [mg KOH/g]	VISCOSITY 23 °C [mPa.s]	DESCRIPTION
DOMACRYL 503	55 X / BAc / nB	10 – 15		1700 – 2600	Basecoat resin.
DOMACRYL 504	60 X / BAc	max. 10	55 – 65	5500 – 7500	Resin for very elastic basecoat and pigment paste. Good compatibility with other OH acrylic resins.
DOMACRYL 536	60 X	max. 10	75 – 100	1300 – 2300	Standard resin for clear and top coats. Available also in BAc and SA.
DOMACRYL 5705	60 X	5 – 10	85 – 105	3000 – 4000	Standard resin. Good adhesion, hardness, gloss and elasticity.
DOMACRYL 5130	70 BAc	6 – 10	90 – 110	4000 – 6000	Broad compatibility with similar acrylic resins. Good balance between hardness and flexibility.
DOMACRYL 521	60 X	max. 10	100 – 120	1400 – 1600	Standard high gloss resin. Good adhesion on different substrates.
DOMACRYL 5210	75 BAc	7 – 11	110 – 130	5000 – 8500	High solid top and clear coats.
DOMACRYL 547	60 X / SA / BAc	10 – 16	110 – 130	2500 – 3500	Rapid initial drying.
DOMACRYL 5475	65 X / BAc	5 – 12	120 – 140	3500 – 4500	Fast drying.
DOMACRYL 5187	70 BAc	max. 15	130 – 145	2800 – 4200	Broad compatibility with similar acrylic resins. Good balance between hardness and flexibility, with excellent mechanical properties and superior outdoor durability and solvent resistance.
DOMACRYL 5503	75 BAc	max. 12	130 – 145	5000 – 7000	Fast drying. Excellent mechanical properties and superior outdoor durability. 25% bio-based on solid content.
DOMACRYL 5108	80 BAc	max. 16	130 – 150	4000 – 8000	Very high solid.
DOMACRYL 5155	60 X / SA / BAc	max. 10	130 – 150	3000 – 4000	High abrasion resistance, high resistance to chemicals and water.
DOMACRYL 5481	75 BAc	max. 12	130 – 150	4500 – 6000	Excellent pigment wetting. CAB compatible.
DOMACRYL 549	70 X / BAc	9 – 15	130 – 150	2500 – 4000	Fast drying.
DOMACRYL 5485	75 BAc	max. 12	135 – 155	8000 – 12000	Excellent resistance and weather stability. CAB compatible. 10% bio-based on solid content.
DOMACRYL 5495	70 X / BAc	5 – 13	135 – 155	1200 – 2400	Good balance between hardness and flexibility. Excellent mechanical properties and superior outdoor durability.
DOMACRYL 5500	75 BAc	8 – 12	140 – 160	3500 – 10000	Very good balance between hardness and flexibility. Excellent mechanical properties and superior chemical resistance.
DOMACRYL 522	60 X / MPA	18 – 25	140 – 160	4000 – 5000	Very good gloss retention and superior outdoor durability.
DOMACRYL 522	60 X / SA / BAc	max. 10	140 – 160	4000 – 6000	Standard high-performance resin.
DOMACRYL 526	70 BAc	max. 8	140 – 160	7000 – 11000	Standard high-performance resin.
DOMACRYL 5415	70 BAc	max. 12	140 – 160	3600 – 6000	Top performance resin.
DOMACRYL 544	60 X / SA / BAc	max. 12	140 – 160	3500 – 8000	Fast drying. Also for primers including plastics.
DOMACRYL 543	60 X / SA / BAc	8 – 14	145 – 165	2300 – 2800	Standard high-performance resin.
DOMACRYL 543	60 X / MPA	8 – 14	145 – 165	2000 – 2500	Standard high-performance resin.
DOMACRYL 5150	75 BAc	2 – 15	145 – 170	3500 – 6500	Excellent chemical and petrol resistance, good weathering and yellowing resistance.

ACRYLIC SOLVENTBORNE SPECIALITIES

RESIN	DELIVERY FORM	ACID VALUE on solid resin [mg KOH/g]	HYDROXYL VALUE on solid resin [mg KOH/g]	VISCOSITY 23 °C [mPa.s]	DESCRIPTION
DOMACRYL 5109	85 BA _c / Ac	max. 10	135 – 155	8000 – 12000	Clear and pigmented top coats. Good balance between hardness and flexibility, with excellent mechanical properties and superior outdoor durability. Suitable for DTM.
DOMACRYL 5270	75 BA _c	max. 3	125 – 145	4000 – 6000	Very long pot-life and super-fast hardness development. Very good balance between hardness and flexibility, with excellent mechanical properties and superior outdoor durability. PATENT PENDING
DOMACRYL 5245	75 BA _c	max. 3	125 – 145	2000 – 5000	Extremely fast drying and long pot-life. Superior mechanical properties and outdoor durability. 17% bio-based on solid content. PATENT PENDING
DOMACRYL 580	67 BA _c	4 – 8	110 – 130	3000 – 6000	Clear and top coats with very long pot-life and super-fast hardness development at room temperatures and forced drying. PATENT PENDING
DOMACRYL 5451	50 BA _c	max. 3	55 – 70	4000 – 6000	Extremely fast drying fillers. PATENT PENDING
DOMACRYL 5220	45 BA _c / X	6 – 12	30 – 40	2000 – 6000	Very good adhesion on plastic substrates (PP, PE, PVC) with good balance between hardness and flexibility.
DOMACRYL 872	60 X	8 – 12		10000 – 15000	Pigmented and transparent paints for plastic. Rapid drying and excellent toughness. T _g = 50 °C.

ALKYD SOLVENTBORNE RESINS

RESIN	DELIVERY FORM	OIL LENGTH / OIL TYPE	ACID VALUE on solid resin [mg KOH/g]	VISCOSITY 23 °C [mPa.s]	DESCRIPTION
DOMALKYD 1468	50 Solvent mix	46% Non-yellowing FA	max. 12	660 – 1000	Very fast surface and through-drying with high gloss and resistance to yellowing.
DOMALKYD 1482	55 W / X	48% Soyabean FA	max. 12	5000 – 7000	Standard resin with very good overall properties. Air and forced drying.
DOMALKYD 1526	55 W	52% Soyabean oil	max. 15	2000 – 3000	Pigment pastes for combination with medium oil air-drying alkyd resins with excellent weather resistance.

POLYESTER SOLVENTBORNE RESINS

RESIN	DELIVERY FORM	ACID VALUE on solid resin [mg KOH/g]	HYDROXYL VALUE on solid resin [mg KOH/g]	VISCOSITY 23 °C [mPa.s]	DESCRIPTION
DOMOPOL 5193	70 X	max. 12	95 – 105	2000 – 3000	Primer surfacers and metallic base coats.
DOMOPOL 6028	78 BA _c	20 – 25	220 – 250	8000 – 13000	Clear and pigmented top coats with high hardness and excellent solvent and chemical resistance.
DOMOPOL 6052	80 BA _c	max. 3	150 – 200	1000 – 2000	For 2K polyurethane coatings as a combination resin for hydroxyl acrylic resins to increase solids content, improve flexibility and outdoor durability in industrial finishes, protective coatings and coatings for plastics.
DOMOPOL 6067	80 BA _c	max. 2	130 – 160	1800 – 2600	Can be added to 2K PUR systems to improve their flexibility.

ACRYLIC AND POLYESTER WATERBORNE RESINS

RESIN	DELIVERY FORM	ACID VALUE on solid resin [mg KOH/g]	HYDROXYL VALUE on solid resin [mg KOH/g]	VISCOSITY 23 °C [mPa.s]	pH	DESCRIPTION
DOMACRYL 0768	42 Wa / PnB	20 – 30	130 – 150	200 – 5000	8.0 – 9.0	Acrylic secondary dispersion. Standard resin for 2K PUR systems. High gloss, without aromatic co-solvent.
DOMEMUL RA 9675	35 Wa	20 – 30		50 – 1000	6.0 – 7.0	Acrylic APEO-free latex resin for effect pigmented coatings (metallic, pearlescent). Basecoat resin.
DOMOPOL 5301	60 BG	24 – 28	85 – 95	1300 – 2700		Milling resin. Water-thinnable after neutralization. Good pigment wetting and adhesion.



ISO 9001
ISO 14001

BUREAU VERITAS
Certification



KANSAI HELIOS Slovenija d.o.o.
Količevo 65, 1230 Domžale, Slovenia
T +386 1 722 40 71
T +386 1 722 43 94
info@resinshelios.com
www.resinshelios.com

ATCOAT GmbH
Katharinenstr. 61, 52353 Düren, Germany
T +49 2421 9999 0
F +49 2421 9999 233
info@atcoat.com
www.atcoat.com