

Product code: 479356

DOMACRYL 5150 75 BAc

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	74 - 76%	MH1155 / ISO 3251
Acid value on solid resin	2 - 15 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	145 - 170 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	3500 - 6500 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	25 °C
Hydroxyl content on solid	5%
Water content	max. 0.1 wt.%

Solubility:

Soluble in aromatic hydrocarbons, glycol ethers, glycol esters and dibasic esters.

Applications:

- » Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins.
- » It has a broad compatibility with similar acrylic resins.
- » Supply form in butyl acetate is suitable for aromatic-free systems and gives high solids system at spraying viscosity (VOC ≤ 420 g/l).
- » Paints based on Domacryl 5150 75 BAc have good balance between hardness and flexibility with excellent mechanical properties and superior outdoor durability.
- » Used for room temperature drying or forced drying of two-pack systems for automotive refinishing (clear and pigmented top coats).
- » Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00, F +386 1 722 43 10
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.