TECHNICAL DATA SHEET



Product code: 402623

DOMACRYL 5154 80 BAc

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	78 - 82%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	60 - 80 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	7000 - 11000 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	30 °C
Hydroxyl content on solid	2.1%
Water content	max. 0.1 wt.%

Solubility:

Soluble in xylene, toluene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate, and methyl isobutyl ketone.

Compatibility:

Compatible with isocyanate resins: HDI- isocyanurate, HDI-biuret and majority of other hydroxy acrylic binders.

Applications:

- Reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins.
- >> Used for room temperature drying or forced drying two-pack protective systems (top and clear coats) with good mechanical properties and outdoor durability.
- Supply form in butyl acetate is suitable for aromatic-free systems and gives high solids system at spraying viscosity (VOC ≤ 350 g/l).
- >> Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023