# TECHNICAL DATA SHEET



Product code: 470263

# DOMACRYL 5267 60 X/MPA

# **Hydroxy Acrylic Resin**

#### Specification:

| Property                      | Range             | Method / According to standard |
|-------------------------------|-------------------|--------------------------------|
| Non-volatile matter           | 59 - 61%          | MH1155 / ISO 3251              |
| Acid value on solid resin     | max. 10 mg KOH/g  | MH1051 / ISO 2114              |
| Hydroxyl value on solid resin | 90 - 110 mg KOH/g | MH1052 / ISO 4629              |
| Viscosity, 23 °C              | 4000 - 6000 mPa·s | MH1007 / ISO 3219              |
| Colour                        | max. 100 APHA     | MH1125 / ISO 6271              |

#### **Typical properties:**

| Property                  | Value                                   |
|---------------------------|---|
| Solvent ratio             | Xylene / Methoxy propyl acetate = 3 / 1 |
| Density                   | 1 kg/L                                  |
| Flash point               | 24 °C                                   |
| Hydroxyl content on solid | 2.8%                                    |
| Water content             | max. 0.1 wt.%                           |

# Solubility:

- >> Soluble in xylene, toluene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate, methyl isobutyl ketone.
- >> Limited solubility in aromatic solvent 100.

# Compatibility:

- Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret, Desmodur L 75, Desmodur IL, Desmodur HL and nitrocellulose (ester soluble).
- Very limited compatibility with CAB.

# **Applications:**

- >> Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins.
- Very good gloss retention and outdoor durability.
- Used for air drying topcoats for metal and ACE coatings.
- Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

## Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023