

Product code: 418960

DOMACRYL 536 60 SA

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	75 - 100 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	2300 - 3300 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	40 °C
Hydroxyl content on solid	2.7%
Water content	max. 0.1 wt.%

Solubility:

Soluble in aromatic solvent 100, aromatic solvent 150, xylene, toluene, acetone, ethyl acetate, n-butyl acetate, n-butanol, methoxy propyl acetate and methyl isobutyl ketone.

Compatibility:

Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret, Desmodur Z 4470 and other binders: nitrocellulose (ester soluble), melamine resins.

Applications:

- » Domacryl 536 60 SA is intended for crosslinking with isocyanate resins for two-component air and forced drying protective top coats.
- » Enamels based on Domacryl 536 60 SA gives films with good adhesion on different substrates, hardness, gloss and elasticity.
- » They are suitable for two-component car repair top coats, agricultural machinery and high-grade industrial paints.
- » Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.