

Product code: 419928

DOMACRYL 5428 70 BA_c

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	69 - 71%	MH1155 / ISO 3251
Acid value on solid resin	max. 15 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	80 - 100 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	1500 - 2500 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	24 °C
Hydroxyl content on solid	2.8%
Water content	max. 0.1 wt.%

Solubility:

Soluble in aromatic solvent 100, aromatic solvent 150, xylene, toluene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate and methyl isobutyl ketone.

Compatibility:

- » Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret and other binders: Vinyl VAGH, nitrocellulose (ester soluble), majority of other Domacryl hydroxy resins.
- » Limited compatibility with CAB 551-0.2.

Applications:

- » Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins.
- » Fast hardness build-up.
- » Used for room temperature drying or forced drying of two-pack systems for automotive refinishing (top and clear coats) with excellent mechanical properties and superior outdoor durability.
- » Supply form in butyl acetate is suitable for aromatic-free systems and is appropriate for high solid system at spraying viscosity.
- » Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing. Physical drying can be accelerated with the addition of CAB resins.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: July 2019

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00, F +386 1 722 43 10
 info@resinshelios.com | www.resinshelios.com
 Member of HELIOS. Part of KANSAI PAINT.