

Product code: 418806

DOMACRYL 547 60 X/SA/BAc

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	10 - 16 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	110 - 130 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	2500 - 3500 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Solvent ratio	Xylene / Aromatic solvent 100 / Butyl acetate = 2 / 1 / 1
Density	1 kg/L
Flash point	27 °C
Hydroxyl content on solid	3.6%
Water content	max. 0.1 wt.%

Solubility:

- >> Soluble in xylene, toluene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate, and methyl isobutyl ketone.
- Limited solubility in aromatic solvent 100 and aromatic solvent 150.

Compatibility:

- Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret, Desmodur L 75 and other binders: Vinyl VAGH, nitrocellulose (ester soluble), Domalkyd 5571, Domopol 6067, majority of other Domacryl hydroxy resins.
- Limited compatibility with CAB 551-0.2.

Applications:

- Highly reactive hydroxy acrylic resin with high initial drying, intended for crosslinking with isocyanate resins.
- >> Used for room temperature drying or forced drying of two-pack systems for automotive refinishing, high grade industrial paints and primer surfaces.
- Rapid initial drying, excellent mechanical properties and chemical resistance.
- >> Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023