

Product code: 477123

DOMACRYL 5485 75 BAc Hydroxy Acrylic Resin



Specification:

Property	Range	Method / According to standard
Non-volatile matter	74 - 76%	MH1155 / ISO 3251
Acid value on solid resin	max. 12 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	135 - 155 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	8000 - 12000 mPa·s	MH1007 / ISO 3219
Colour	max. 50 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	25 °C
Hydroxyl content on solid	4.2%
Water content	max. 0.1 wt.%
Bio-based content on solid	10%
Total renewable content on delivery form	7.5%

Solubility:

- Soluble in xylene, toluene, acetone, ethyl acetate, n-Butyl acetate, methoxy propyl acetate and methyl isobutyl ketone.
- >> Limited solubility in aromatic solvent 100 and aromatic solvent 150.

Compatibility:

Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret, and other binders: Vinyl VAGH, nitrocellulose (ester soluble), majority of other Domacryl hydroxy resins.

Applications:

- >> Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins. It has a broad compatibility with similar acrylic resins.
- Coatings based on Domacryl 5485 75 BAc have good balance between hardness and flexibility, with excellent mechanical properties and superior outdoor durability.
- Used for room temperature drying or forced drying two-pack systems for automotive refinishing (clear and pigmented top coats).
- Supply form in butyl acetate is suitable for aromatic-free systems and gives high solids system at spraying viscosity (VOC ≤ 420 g/l).
- Suitable for DTM (direct-to-metal) application.
- >> Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing. Physical drying can be accelerated with the addition of CAB resins.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024