

Product code: 479386

DOMACRYL 855 60 T

Thermoplastic Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	5 - 10 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	800 - 2000 mPa·s	MH1007 / ISO 3219

Typical properties:

Property	Value
Tg	-4 °C

Solubility:

Soluble in aromatic and aliphatic hydrocarbons, esters and ketones.

Applications:

- » Domacryl 855 60 T is an air drying polyacrylic resin for the preparation of the pigmented and transparent paint.
- » Recommended is for spray-application paint for road marking, with good adhesion to asphalt, concrete and metal.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 24 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: October 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.