

Product code: 479342

DOMACRYL 920

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 °C	100 - 130 mPa·s	MH1007 / ISO 3219

Typical properties:

Property	Value
Appearance	Bluish opaque liquid
Refractive index	1.44

Remarks:

- » Low viscosity, fast curing methacrylate resin, used for permanent cold spray plastic road markings.
- » Markings based on Domacryl 920 are permanently elastic, weather resistant and resistant to abrasion, road salts and fuels.
- » Domacryl 920 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- » Domacryl 920 is amine pre-activated.

Applications:

- » Binder for cold spray plastic road markings, hardened with dibenzoyl peroxide.
- » Particularly suitable for spray application (drop-on-procedure) with reactive glass beads in the 100:2 systems with special spray machines and 1:1 system with Domacryl 922 which is not pre-accelerated.
- » Recommended layer thickness is 0.4 - 0.8 mm.
- » Recommended application temperature is between 5 and 40 °C.
- » Domacryl 920 has a mild odour.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.