

Product code: 402624

DOMACRYL 9922

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 °C	80 - 100 mPa·s	MH1007 / ISO 3219

Typical properties:

Property	Value
Appearance	Opaque liquid

Remarks:

- » Low viscous, hard methacrylate resin used for flooring.
- » Domacryl 9922 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- » Domacryl 9922 is amine pre-activated.

Applications:

- » Reactive 2-pack methacrylate resin, hardened with dibenzoyl peroxide.
- » For proper curing at 20 °C add 2% hardener in respect to resin. For different temperatures, adjust hardener amount.
- » Suitable for adhesive primers for concrete and cement screeds.
- » Application with rollers and squeegee.
- » Typical consumption: 0,4 kg/m²

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.