TECHNICAL DATA SHEET



Product code: 471174

DOMACRYL 992

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 °C	100 - 140 mPa·s	MH1007 / ISO 3219
Colour	max. 1 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Opaque liquid
Refractive index	1.44

Remarks:

- Domacryl 992 is a methacrylate resin, used for permanent cold plastic markings with good wetting properties for fillers and pigments.
- Markings based on Domacryl 992 are very elastic, weather resistant and resistant to abrasion, road salts and fuels.
- Domacryl 992 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- Domacryl 992 is amine pre-activated.

Applications:

- Binder for two component road markings, hardened with dibenzoyl peroxide.
- >> Used for marking of pedestrian crossings, stop lines, direction arrows and safety markings with increased night visibility.
- >> Particularly suitable for manual application with smoothing trowels or draw box machines.
- Recommended layer thickness is 1 2 mm.
- Recommended application temperature is between 5 and 35 °C.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.