TECHNICAL DATA SHEET



Product code: 481194

DOMALKYD 0246 70 BGWater Reducible Epoxy Modified Alkyd Resin



Specification:

Property	Range	Method / According to standard
Non-volatile matter	68 - 72%	MH1155 / ISO 3251
Acid value on solid resin	35 - 65 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	8000 - 22000 mPa·s	MH1007 / ISO 3219

Typical properties:

Property	Value
Solvent ratio	Butylglycol / Methoxypropanol = 70 / 30
Density	1.1 kg/L
Oil content	23%
Bio-based content on solid	42%
Total renewable content on delivery form	29%

Remarks:

- The bio-based content is 23% of the dry matter by the Carbon-14 method and an additional 19% via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- >> Water reducible after neutralization with amine.
- >> Partially neutralized with dimethylethanolamine.

Compatibility:

Compatible with most water reducible resins and water reducible melamine resins.

Applications:

- Used for non air-drying corrosion protection primers and top coats.
- Crosslinked with melamine resins it is used for durable stoving systems
- >> Coating systems based on Domalkyd 0246 70 BG have excellent pigment wetting, very good corrosion properties, high reactivity, high hardness and high flexibility in stoving systems.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024