

Product code: 477546

DOMALKYD 0261 70 PnB/2B

Water Reducible Alkyd Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	69 - 71%	MH1155 / ISO 3251
Acid value on solid resin	35 - 45 mg KOH/g	MH1051 / ISO 2114
Viscosity, 25 °C	5000 - 15000 mPa·s	MH1007 / ISO 3219
Colour	max. 8 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Solvent ratio	Propyleneglycol n-Butyl eter / 2-Butanol = 1 / 1
Oil content	28%
Bio-based content on solid	61%
Total renewable content on delivery form	43%

Remarks:

- » The bio-based content is 28% of the dry matter by the Carbon-14 method and an additional 33% via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- » Water reducible after neutralization.
- » Neutralization with ammonia or amines to pH 8 - 8.5 prior to dilution with water.
- » To improve paint stability 10 - 20% (calculated on solid resin) cosolvent must be added.
- » For baking systems Domalkyd 0261 70 PnB/2B must be blended with water reducible melamine resin (approx. 20% solid on solid). Baking conditions depends on reactivity of melamine resin.

Compatibility:

Compatible with water reducible resins, water reducible melamine resins and with some acrylic dispersion; combinations will improve drying properties, adhesion on different materials and layer structure.

Applications:

Domalkyd 0261 70 PnB/2B is used for primers and top coats for industrial application (air and forced drying and stowing systems) with excellent corrosion resistance.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.