

Product code: 479364

DOMALKYD 0391 80 Wa/BG
Water Thinnable Alkyd Resin**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	78 - 82%	MH1155 / ISO 3251
Acid value on solid resin	40 - 50 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	30000 - 60000 mPa·s	MH1007 / ISO 3219
pH (diluted with 3x water)	7 - 9	MH1040 / ISO 976
Colour	max. 6 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Clear to slightly cloudy
Solvent ratio	Water / Butylglycol / Dimethyl ethanol amine = 14 / 1.5 / 4.5
Density	1.1 kg/L
Flash point	>100 °C
Hydroxyl content on solid	6.5%
Oil content	35%
Bio-based content on solid	66%
Total renewable content on delivery form	67%

Remarks:

- » The bio-based content is 35% of the dry matter by the Carbon-14 method and an additional 31% via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- » Domalkyd 0391 80 Wa/BG is further reducible with water up to 50% solid content.
- » During storage the pH value of resin can decrease. This can cause the viscosity decrease and the hazy aspect of the resin. This is reversible. The pH value can be increased again by the addition of DMEA or another suitable amine. Once the pH value rises, the resin will clear.
- » Storage for longer periods of time and/or at higher temperatures may result in a decrease of viscosity and/or sedimentation or coagulation.

Applications:

- » Used for primers and top coats with less than 2% co-solvent.
- » Very suitable for drums.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid exposure to direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.