

Product code: 471165

DOMALKYD 0545 40 Wa
Urethane Modified Alkyd Resin**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	39 - 41%	MH1155 / ISO 3251
Acid value on solid resin	max. 28 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	50 - 1000 mPa·s	MH1007 / ISO 3219
pH	7 - 8	MH1040 / ISO 976

Typical properties:

Property	Value
Density	1.0 kg/L
Oil content	44%
Hydroxyl content on solid	1%
Bio-based content on solid	70%
Total renewable content on delivery form	88%

Remarks:

The bio-based content is 47% of the dry matter by the Carbon-14 method and an additional 23% via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Compatibility:

Compatible with many water reducible alkyds and alkyd emulsions, and with most acrylic dispersions.

Applications:

- » Used for yellowing-resistant top coats and one-coat paints for industrial application (air and forced drying) on wood, steel and aluminium with excellent gloss retention and elasticity.
- » Domalkyd 0545 40 Wa contains no emulsifiers and may be thinned with water at all ratios.
- » Coating systems based on Domalkyd 0545 40 Wa exhibit very rapid physical drying. However, use of water-based dryer is advisable. Dryer should be added slowly under agitation.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid exposure to direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.