

Product code: 470256

DOMALKYD 1272 60 X

Alkyd Resin Modified with Soybean Fatty Acids

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	2000 - 3000 mPa·s	MH1007 / ISO 3219
Colour	max. 5 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Oil content	27%

Solubility:

- » Soluble in aromatic hydrocarbons, esters, ketones and glycol ethers.
- » Limited solubility in alcohols and aliphatic hydrocarbons.

Compatibility:

Compatible with most short and some medium oil alkyd resins, nitrocellulose, vinyl, melamine and urea resins.

Applications:

- » Used as a universal fast drying resin for air and forced drying industrial primers and high build finishes for metal.
- » It excels in rapid drying, high gloss and good yellowing stability.
- » In combination with vinyl resins, paints are very fast drying.
- » Combinations with reactive melamine resins are suitable for forced drying systems.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.