

Product code: 418814

DOMALKYD 1361 60 X

Alkyd Resin Modified with Soybean Fatty Acids

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	4400 - 5600 mPa·s	MH1007 / ISO 3219
Colour	max. 6 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Oil content	34%

Solubility:

- » Soluble in aromatic and terpene hydrocarbons, esters, ketones and glycol ethers.
- » Limited solubility in aliphatic hydrocarbons.
- » Insoluble in alcohols.

Compatibility:

- » Compatible with most medium oil air drying alkyds, cyclized rubber and nitrocellulose.
- » Incompatible with most stoving and non-oxidizing alkyds, vinyl copolymers and polymerized oils.

Applications:

- » Used for primers, putties and industrial finishes.
- » Due to special fatty acids content very good drying properties are attained and low yellowing by air drying.
- » It excels in good outdoor durability and adhesion to metals.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.