

Product code: 409844

## DOMALKYD 1482 55 W/X

### Alkyd Resin Modified with Soybean Fatty Acids

**Specification:**

| Property                  | Range             | Method / According to standard |
|---------------------------|-------------------|--------------------------------|
| Non-volatile matter       | 54 - 56%          | MH1155 / ISO 3251              |
| Acid value on solid resin | max. 12 mg KOH/g  | MH1051 / ISO 2114              |
| Viscosity, 23 °C          | 5000 - 7000 mPa·s | MH1007 / ISO 3219              |
| Colour                    | max. 6 Gardner    | MH1124 / ISO 4630              |

**Typical properties:**

| Property      | Value                           |
|---------------|---------------------------------|
| Solvent ratio | White spirit / Xylene = 70 / 30 |
| Oil content   | 48%                             |

**Solubility:**

- » Soluble in aromatic and terpene hydrocarbons, esters, ketones and glycol ethers.
- » Limited solubility in aliphatic hydrocarbons.
- » Insoluble in alcohols.

**Compatibility:**

- » Compatible with most long and medium oil air drying alkyd resins and cyclized rubber.
- » Incompatible with most stoving and non-oxidizing alkyds, vinyl copolymers and polymerized oils.

**Applications:**

- » Domalkyd 1482 55 W/X is mostly used in automotive repair finishes and paints for metal work.
- » Due to special fatty acids content very good drying properties are attained and low yellowing by air drying.
- » By forced drying (at 80 °C) a combination with melamine resins provides higher gloss and film hardness.

**Storage:**

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 24 months. Exposure to direct sunlight should be avoided.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00  
info@resinshelios.com | [www.resinshelios.com](http://www.resinshelios.com)  
Part of KANSAI PAINT.