

Product code: 470262

DOMALKYD 4383 70 BA_c

Alkyd Resin Modified with Soybean Oil

Specification:

Property	Range	Method / According to standard
Non-volatile matter	69 - 71%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	3000 - 4500 mPa·s	MH1007 / ISO 3219
Colour	max. 6 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Oil content	38%

Solubility:

Soluble in aromatic hydrocarbons, esters, ketones and higher alcohols.

Compatibility:

- » Compatible with short oil alkyd resins, nitrocellulose, phthalate plasticizers and amino resins.
- » Incompatible with long- and some medium-oil air drying alkyds and drying oils.

Applications:

- » Used in lacquers and enamels for wood in combination with nitrocellulose, acid curing lacquers and in high quality NC combination coatings.
- » When combined with amino resins it is used for stoving enamels.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.