

Product code: 419696

DOMALKYD 7351 60 X

Polyurethane Resin Modified with Soybean Fatty Acids

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	6 - 15 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	4000 - 7000 mPa·s	MH1007 / ISO 3219
Colour	max. 6 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Oil content	35%
Type of Isocyanate	Aromatic

Solubility:

Soluble in aromatic hydrocarbons, esters and ketones.

Compatibility:

Compatible with short and medium oil air drying alkyd resins.

Applications:

Domalkyd 7351 60 X is used in the preparation of very fast air-drying enamels for industrial applications and traffic paints.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.