

Product code: 418950

DOMALKYD 7625 60 D-40

Polyurethane Resin Modified with Soybean Oil

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 5 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	2200 - 2800 mPa·s	MH1007 / ISO 3219
Colour	max. 6 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Oil content	62%
Type of Isocyanate	Aromatic

Solubility:

- » Soluble in aromatic and aliphatic hydrocarbons, esters and ketones.
- » Limited solubility in glycol ethers and higher alcohols.
- » Insoluble in lower alcohols.

Compatibility:

- » Compatible with medium and long oil alkyd resins, polymerized oils and hard resins.
- » Well compatible with basic pigments.

Applications:

- » Domalkyd 7625 60 D-40 is used alone or in combination with long and medium oil alkyd resins in the preparation of universal finishes for wood.
- » It is specially recommended for finishes for floors, boats and furniture.
- » It dries quickly, has good chemical and water resistance and gives excellent anticorrosion primers and aluminium paints for steel.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.