

Product code: 470253

## DOMEMUL AA 9670

### APEO-free Acrylic Emulsion

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	39 - 41%	MH1155 / ISO 3251
Viscosity, 23 °C	100 - 800 mPa·s	MH1007 / ISO 3219
pH	7.5 - 9.5	MH1040 / ISO 976

**Typical properties:**

Property	Value
Solvent	Water
Appearance	Brownish
Density	1.1 kg/L
MFFT	0 °C

**Applications:**

- » Used for industrial waterborne wood coatings, interior and exterior.
- » Recommended for furniture, joinery and decorative application with non-yellowing, good wetting good water-resistance, low-foaming, flow, transparency and good blocking resistance.

**Storage:**

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid direct sunlight.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00  
info@resinshelios.com | [www.resinshelios.com](http://www.resinshelios.com)  
Part of KANSAI PAINT.