TECHNICAL DATA SHEET



Product code: 400346, 401808

DOMEMUL AA 9674

Self-crosslinking APEO-free Acrylic Emulsion with OH-functionality

Specification:

Property	Range	Method / According to standard
Non-volatile matter	40 - 42%	MH1155 / ISO 3251
Viscosity, 23 °C	20 - 500 mPa·s	MH1007 / ISO 3219
рН	7 - 8	MH1040 / ISO 976

Typical properties:

Property	Value	
Solvent	Water	
Appearance	Bluish white	
Density	1.0 kg/L	
MFFT	50 °C	
Hydroxyl content on solid	1.8%	
	Option A (product code 400346): 3.5 ppm MIT; 11 ppm CIT; 110 ppm	
Biocide content	Bronopol	
	Option B (product code 401808): 375 ppm BIT; 14 ppm CIT/MIT (3/1)	

Compatibility:

>> Compatible with similar acrylic dispersions and polyurethane dispersions.

Applications:

- >> Designed for industrial waterborne wood coatings for interior.
- 1K and 2K wood varnishes.
- Specially recommended for furniture and joinery non-yellowing enamels with good water, chemical and blocking resistance.
- Suitable for high gloss and matt formulations.
- >> To lower MFFT use of a coalescent (butyl glycol, dipropylene glycol methyl ether and/or Texanol) is advised.
- Starting formulations available on demand.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023