TECHNICAL DATA SHEET



Product code: 479375

DOMEMUL RA 9675

APEO-free Acrylic Latex

Specification:

Property	Range	Method / According to standard
Non-volatile matter	34 - 36%	MH1155 / ISO 3251
Viscosity, 23 °C	50 - 1000 mPa·s	MH1007 / ISO 3219
рН	6 - 7	MH1040 / ISO 976

Typical properties:

Property	Value
Solvent	Water
Appearance	Milky white, bluish
Density	1.0 kg/L
Conductivity	2 mS/cm
MFFT	0 °C

Applications:

- >> Used for the preparation of industrial aluminum-pigmented aqueous basecoats.
- Pseudoplastic rheology profile ensures great metallic appearance.
- >> It can be combined with other latexes, alkyd-dispersions, PUDs and water-soluble polyesters.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.