

Product code: 472090

## DOMEMUL SA 9262 APEO-free

### APEO-free Styrene-acrylic Emulsion

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	41 - 43%	MH1155 / ISO 3251
Viscosity, 23 °C	50 - 250 mPa·s	MH1007 / ISO 3219
pH	8.0 - 8.5	MH1040 / ISO 976

**Typical properties:**

Property	Value
Solvent	Water
Appearance	Milky white
Density	1.0 kg/L
MFFT	30 °C

**Remarks:**

Domemul SA 9262 APEO-free, can be combined with urethanes and alkyds.

**Applications:**

- » Designed for industrial waterborne coatings: anticorrosive primers, metal finishes, plastic and wood.
- » Recommended for application with good adhesion to metal and good humidity resistance.

**Storage:**

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 12 months. Protect from freezing and avoid direct sunlight.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** June 2023

**Helios TBLUS, d.o.o.** | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00  
info@resinshelios.com | [www.resinshelios.com](http://www.resinshelios.com)  
Part of KANSAI PAINT.