

Product code: 470255

DOMEMUL SA 9263

Styrene-acrylic APEO-free Emulsion

Specification:

Property	Range	Method / According to standard
Non-volatile matter	39 - 41%	MH1155 / ISO 3251
Viscosity, 23 °C	20 - 350 mPa·s	MH1007 / ISO 3219
pH	8.0 - 8.5	MH1040 / ISO 976

Typical properties:

Property	Value
Solvent	Water
Appearance	Milky white
Density	1.0 kg/L
MFFT	45 °C

Remarks:

Domemul SA 9263 can be combined with urethanes, epoxy esters and alkyds.

Applications:

- » Designed for industrial waterborne coatings: anticorrosive primers, metal finishes, plastic and wood.
- » Recommended for application with good adhesion to metal, good humidity resistance and high gloss.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.