

Product code: Provisional

DOMOPOL 0194 45 Wa

Water-thinnable Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	44 - 46%	MH1155 / ISO 3251
Acid value on solid resin	50 - 60 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	300 - 1500 mPa·s	MH1007 / ISO 3219
pH	7 - 9	MH1040 / ISO 976
Colour	max. 2 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Clear to slightly cloudy
Density	1.0 kg/L
Flash point	100 °C
Hydroxyl content on solid	3%
Bio-based content on solid	14%
Total renewable content on delivery form	56%

Remarks:

- » The bio-based content is 14% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- » Contains no organic solvent.
- » Neutralised with dimethyl ethanol amine. Ratio water / DMEA is app. 50 / 5.

Applications:

- » Domopol 0194 45 Wa is suitable for the formulation of base coats and top coats.
- » Special properties are high gloss, good weatherability, along with high thermal stability.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid exposure to direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.