TECHNICAL DATA SHEET



Product code: 402612

DOMOPOL 0358 70 Wa/BDGWater-thinnable Saturated Polyester Resin





Specification:

Property	Range	Method / According to standard
Non-volatile matter	69 - 71%	MH1155 / ISO 3251
Acid value on solid resin	40 - 60 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	15000 - 25000 mPa·s	MH1007 / ISO 3219
рН	7 - 9	MH1040 / ISO 976
Colour	max. 2 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Cosolvent	Butyldiglycol
Appearance	Clear to slightly cloudy
Density	1.1 kg/L
Flash point	110 °C
Hydroxyl content on solid	3%
Bio-based content on solid	16%
Total renewable content on delivery form	25%

Remarks:

- >> The bio-based content is 16% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- >> Neutralised with dimethyl ethanol amine.
- >> Ratio water / BDG / DMEA (as a salt) is approximately 14.2 / 11 / 4.8.

Applications:

Domopol 0358 70 Wa/BDG is used in combination with water dillutable amino resins for the production of low-co-solvent industrial stoving lacquers and hydro-stoving filler for automotive OEM finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 12 months. Protect from freezing and avoid exposure to direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024