

Product code: 419930

DOMOPOL 5117 60 SAB ND
Saturated Polyester Resin**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	5 - 10 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	22 - 30 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	14000 - 18000 mPa·s	MH1007 / ISO 3219
Colour	max. 2 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Density	1.1 kg/L
Molecular weight	5500
Flash point	63 °C
Hydroxyl content on solid	0.8%
Tg	25 °C
Bio-based content on solid	23%
Total renewable content on delivery form	14%

Remarks:

The bio-based content is 23% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Solubility:

Soluble in aromatic hydrocarbons, esters and glycol ethers.

Compatibility:

Compatible with amino resins and blocked polyisocyanate resins.

Applications:

- » Domopol 5117 60 SAB ND is intended for can coatings – white base coats, tube coating.
- » Principal properties are deep drawn flexibility and cold crush flexibility.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.