

Product code: 471168

DOMOPOL 5130 65 SAB/BG ND

Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	64 - 66%	MH1155 / ISO 3251
Acid value on solid resin	max. 8 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	28 - 36 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	1500 - 3000 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Solvent ratio	Aromatic solvent 150 ND / Butyglycol = 2 / 1
Molecular weight	3500
Flash point	62 °C
Tg	10 °C
Bio-based content on solid	24%
Total renewable content on delivery form	16%

Remarks:

The bio-based content is 24% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Applications:

- » Domopol 5130 65 SAB/BG ND is intended for coil coatings: interior and exterior architecture.
- » This product may also be suitable for appliance finishing applications.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEETCopyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1