# TECHNICAL DATA SHEET



Product code: 472095

# **DOMOPOL 5142 60 SAB/DBE ND**

# **Saturated Polyester Resin**



#### Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 6 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	15 - 25 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	9500 - 13500 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

## **Typical properties:**

Property	Value
Solvent ratio	Aromatic solvent 150 ND / Dibasic esters = 4 / 1
Molecular weight	5000
Flash point	65 °C
Tg	51 °C
Bio-based content on solid	26%
Total renewable content on delivery form	16%

#### Remarks:

The bio-based content is 26% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

#### Solubility:

Soluble in aromatic hydrocarbons, esters and glycol ethers.

#### Compatibility:

Compatible with amino resins and blocked polyisocyanate resins.

## **Applications:**

- >> Domopol 5142 60 SAB/DBE ND is intended for can coating, white base coat.
- >> This product may also be suitable for coil coating primers.
- Principal properties are adhesion, corrosion protection and hardness.

#### Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024