TECHNICAL DATA SHEET



Product code: 472089

DOMOPOL 5148 55%Saturated Polyester Resin





Specification:

Property	Range	Method / According to standard
Non-volatile matter	54 - 56%	MH1155 / ISO 3251
Acid value on solid resin	max. 3 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	35 - 45 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	3600 - 4400 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value	
Solvent ratio	Methoxypropanol / Dipropylene glycol monomethyl ether = 3 / 1	
Molecular weight	4000	
Flash point	64 °C	
Tg	20 °C	
Bio-based content on solid	26%	
Total renewable content on delivery form	14%	

Remarks:

The bio-based content is 26% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Applications:

- >> It is recommended for can coating applications, especially metal decorating enamels. It may also be used for tube and aerosol can coatings.
- >> Overprint varnish based on this resin shows excellent flexibility and wet-on-wet properties.
- Domopol 5148 55% is based on FDA approved raw material for non-alcoholic content (FDA § 175.300).

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.