

Product code: 402648

DOMOPOL 7046 100%

Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	100%	MH1155 / ISO 3251
Acid value on solid resin	7 - 12 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	250 - 290 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	750 - 1000 mPa·s	MH1007 / ISO 3219
Colour	max. 2 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Density	1.1 kg/L
Molecular weight	1000
Bio-based content on solid	100%

Remarks:

The bio-based content is 69% of the dry matter by the Carbon-14 method and an additional 31% via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Solubility:

Soluble in most solvents.

Applications:

- » Domopol 7046 100% is used in 2K polyurethane coatings as such or as a combination resin for hydroxyl acrylic resins to increase solids content in industrial finishes, protective coatings and plastic coatings.
- » Principal properties are high gloss, UV light and heat resistance and weathering resistance.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2024

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.