

Product code: Provisional

## DOMOPOL 8260 65 BG

### Acrylic Modified Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	64 - 66%	MH1155 / ISO 3251
Acid value on solid resin	57 - 63 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	7000 - 11000 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

**Typical properties:**

Property	Value
Flash point	67 °C
Bio-based content on solid	16%
Total renewable content on delivery form	10%

**Remarks:**

- » The bio-based content is 16% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.
- » Water dilutable resin.

**Applications:**

- » Can coating: exterior white basecoat and overprint varnish.
- » Coil coating: primer.
- » Principal properties: flexibility, physical drying and adhesion.

**Storage:**

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** January 2024

**Helios TBLUS, d.o.o.** | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00  
info@resinshelios.com | [www.resinshelios.com](http://www.resinshelios.com)  
Part of KANSAI PAINT.