

Product code: 479388

DOMOPOL 9050 40 SA

High Molecular Weight Polyester Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	39 - 41%	MH1155 / ISO 3251
Acid value on solid resin	0 - 4 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	5 - 10 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	1800 - 3500 mPa·s	MH1007 / ISO 3219
Colour	max. 5 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Clear to slightly hazy
Density	1.1 kg/L
Molecular weight	14000
Flash point	43 °C
Tg	105 °C

Remarks:

Other solvent combinations are possible.

Applications:

- » Interior can coating – epoxy replacement.
- » Principal properties are flexibility, good sterilization resistance and high adhesion.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: June 2023

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00
info@resinshelios.com | www.resinshelios.com
Part of KANSAI PAINT.