

COLGEL GC 610 RAL xxxx

Gel Coat

Description:

- » Colgel GC 610 RAL xxxx iso/NPG gel coats are quality coatings for the fiberglass industry.
- » These gel coats provide quality finishes with good chemical/water resistance, gloss retention, weatherability and resiliency.
- » Colgel GC 610 RAL xxxx is available in a wide range of colours and is ready to use, easy to spray, sag resistant and require only the addition of proper amount of an appropriate MEKP-50 to cure.
- » Colgel GC 610 gel coat may have guaranteed quality for 25 years regarding UV stability.

Specifications at 25 °C:

These values may or may not be manufacturing criteria; they are listed for a reference guide only. Particular batches may not conform exactly to the numbers listed because storage conditions, temperature changes, age, testing equipment (type and procedure) can each have a significant effect on the results. Gel coats with properties outside of these ranges can perform acceptably.

Property	Range	Method / According to standard
Viscosity; #4/10 rpm	7000 - 9000 mPa·s	MH1009 / ISO 3219
Thixotropic index (2.5/20)	5.0 - 7.0	MH1009 / ISO 3219
Gel time with 2% MEKP-50	6 - 12 minutes	MH3021
Monomer content	34 - 38%	MH2034
Density	1.15 - 1.30 kg/L depending on colour	MH1028 / ISO 2811
Color Match	max. DE of 1 unit	MH3311

Physical characteristics of cured nonreinforced base resin:

Property	Range	Method / According to standard
Barcol hardness	41 - 45	EN 59
Tensile strength	80 - 90 MPa	ISO R 527
Elongation at break	3.5 - 5.5%	ISO 178
Flexural strength	130 - 150 MPa	ISO 178
E - modulus in tension	3000 - 3300 MPa	ISO R 527
Heat distortion temperature	90 - 100 °C	ISO 75 A

Application:

- » Colgel GC 610 RAL xxxx gel coat are generally formulated for airless as well as conventional spray application.
- » Brushing or rolling is not recommended.
- » Do not add solvents such as acetone, if required 1 - 3% of styrene may be added to obtain optimum viscosity for special application purpose.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2020

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00, F +386 1 722 43 10
 info@resinshelios.com | www.resinshelios.com
 Member of HELIOS. Part of KANSAI PAINT.

Cure:

- » It is recommended that gel time is checked in the customer's plant, because age, temperature, humidity, and catalyst will produce varied gel times.
- » All data referencing gel or cure refers specifically to AKZO NOBEL Butanox M-50 catalyst.
- » The catalyst level should not exceed 3% or fall below 1.5% for proper cure. Recommended range is 1.8 - 2.2%.
- » This product should not be used when temperature conditions are below 18 °C.

Caution:

- » Do not over mix gel coats. Over-mixing breaks down gel coat viscosity, increasing tendencies to sag and causes styrene loss, which could contribute to porosity.
- » Gel coat should be mixed once a day for 10 minutes. Air bubbling should not be used for mixing.
- » Do not add any material other than a recommended MEKP-50.

Storage:

Uncatalyzed, standard cure gel coats have a usage life of 4 months from date of manufacture when stored at 25 °C or below in a closed container out of direct sunlight.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: January 2020

Helios TBLUS, d.o.o. | Količevo 65, 1230 Domžale, Slovenia | T +386 1 722 40 00, F +386 1 722 43 10
info@resinshelios.com | www.resinshelios.com
Member of HELIOS. Part of KANSAI PAINT.