

COLPOLY 7166

Unsaturated Polyester Resin

Description:

Unsaturated polyester resin based on isophthalic acid and neopentyl glycol (NPG), dissolved in styrene.

Application:

- » Specially formulated resin for tanks, silos and pipes.
- » Colpoly 7166 is used as an adhesion promoter between PVC and GRP in the construction of GRP tanks with PVC liners.

Features and benefits:

- » Excellent mechanical strength.
- » High HDT.
- » Outstanding durability.

Physical characteristics of the liquid resin:

Property	Range	Method / According to standard
Appearance	Clear	
Acid value	10 - 20 mg KOH/g	MH1051 / ISO 2114
Density, 25 °C	1.05 - 1.35 kg/L	MH1028 / ISO 2811
Styrene content	41 - 45%	MH2034
Viscosity, 25 °C	330 - 410 mPa·s	MH1009 / ISO 3219
Flash point	34 °C	DIN 51 755
Shelf life at 25 °C in darkness	6 months	

Curing characteristics at 25 °C:

Property	Range	Method / According to standard
Gel time	20 - 30 minutes	MH3021 / MH3023
Time from 20 °C to peak	10 - 20 minutes	100 g resin, 0.25% Co Acc. 6% 1.5% MEKP-50
Exothermic temperature (peak)	170 - 190 °C	

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: July 2023

Physical characteristics of cured nonreinforced base resin:

Property	Range	Method / According to standard
Density, 20 °C	1.15 - 1.20 kg/L	ISO 1183
Barcol hardness	35 - 45	EN 59
Tensile strength	50 - 70 MPa	ISO R 527
Elongation at break	4.0 - 5.0%	ISO R 527
Flexural strength	70 - 90 MPa	ISO 178
E - modulus in tension	3200 - 3600 MPa	ISO R 527
Water absorption	< 1.5%	ISO 62
Heat distortion temperature	85 - 95 °C	ISO 75 A
Glass transition temperature	100 - 110 °C	ISO 537

Cure:

- » It is recommended that gel time be checked in the customer's plant as age, temperature, humidity and catalyst will produce varied gel times.
- » The catalyst level should not exceed 2.5% or fall below 1.0% for proper cure at ambient temperature.
- » The product should not be used when temperature condition is below 18 °C.

Handling and safety precautions:

Colpoly 7166 is flammable liquid and should be kept away from naked flames. For further details, please see the relevant Safety Data Sheet.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: July 2023