

## COLPOLY 7331 LV

### Unsaturated Polyester Resin

#### Description:

- » Unsaturated polyester resin for GRP, based on dicyclopentadiene and orthophthalic acid dissolved in styrene.
- » Colpoly 7331 LV is preaccelerated, low thixotropic to prevent sedimentation of inorganic fillers. Contains colour change indicator and barrier-forming agents to reduce styrene emission.
- » CAUTION: Prolonged storage or unfavourable storage conditions may cause slight separation, hence agitation of the resin before use is recommended.

#### Application:

- » Resin is formulated to be filled with inorganic fillers and design for use with spray-up systems for lamination to acrylic sheet.
- » WARNING: The large number of substrates which are available on the PMMA/ABS market, we recommend that customers should first carry out an adhesion test on the intended substrate before any industrial application.

#### Features and benefits:

- » Clear excellent mechanical and wetting properties.
- » Rapid cure at low peak exotherm.
- » Good adhesion to acrylics (especially PMMA).
- » Low thixotropic index (1.5 - 2.5; #2, 2.5/20 rpm).

#### Physical characteristics of the liquid resin:

Property	Range	Method / According to standard
Appearance	Blue, opaque	
Acid value	15 - 25 mg KOH/g	MH1051 / ISO 2114
Density, 25 °C	1.04 - 1.08 kg/L	MH1028 / ISO 2811
Styrene content	35 - 39%	MH2034
Viscosity; 25 °C, #2/20 rpm	120 - 160 mPa·s	MH1009 / ISO 3219
Flash point	34 °C	DIN 51 755
Shelf life at 25 °C in darkness	6 months	

#### Curing characteristics at 20 °C:

Property	Range	Method / According to standard
Gel time	8 - 10 minutes	MH3021 / MH3023 2.0% MEKP-50
Time from gel to peak	12 - 18 minutes	
Exothermic temperature (peak)	135 - 155 °C	

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** February 2021

**Physical characteristics of cured nonreinforced base resin:**

Property	Range	Method / According to standard
Density, 20 °C	1.14 - 1.18 kg/L	ISO 1183
Barcol hardness	35 - 45	EN 59
Tensile strength	65 - 70 MPa	ISO R 527
Elongation at break	2.0 - 3.0%	ISO R 527
Flexural strength	90 - 110 MPa	ISO 178
E - modulus in tension	3600 - 3800 MPa	ISO R 527
Impact resistance	10 - 15 kJ/m <sup>2</sup>	ISO 179
Heat distortion temperature	65 - 75 °C	ISO 75 A
Glass transition temperature	90 - 100 °C	ISO 537

**Cure:**

- » It is recommended that gel time be checked in the customer's plant as age, temperature, humidity and catalyst will produce varied gel times.
- » The catalyst level should not exceed 2.5% or fall below 1.0% for proper cure at ambient temperature.
- » The product should not be used when temperature condition is below 18 °C.

**Handling and safety precautions:**

Colpoly 7331 LV is flammable liquid and should be kept away from naked flames. For further details, please see the relevant Safety Data Sheet.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** February 2021