

## COLPOLY 7795

### Unsaturated Polyester Resin

#### Description:

- » Unsaturated polyester resin based on maleic acid and propylene glycol/NPG, dissolved in styrene.
- » The resin can be readily thickened with magnesium oxide.

#### Application:

Resin is designed for use in producing bulk mould compound (BMC), sheet moulding compound (SMC).

#### Features and benefits:

- » »Class A« automotive appearance.
- » Low shrinkage.
- » High gloss.

#### Physical characteristics of the liquid resin:

Property	Range	Method / According to standard
Appearance	Transparent	
Acid value	15 - 20 mg KOH/g	MH1051 / ISO 2114
Density, 25 °C	1.10 - 1.13 kg/L	MH1028 / ISO 2811
Styrene content	34 - 36%	MH2034
Viscosity, 23 °C	1700 - 1900 mPa·s	MH1009 / ISO 3219
Colour	max. 140	MH1125 / ISO 6271
Refractive index, 23 °C	1.518 - 1.521	MH1035 / DIN 51423 P1
Water content	0.05 - 0.15	MH1041
Flash point	34 °C	DIN 51 755
Shelf life at 25 °C in darkness	6 months	

#### Curing characteristics at 140 °C:

Property	Range	Method / According to standard
Time from 40 °C – 14 0°C	40 - 70 seconds	MH3026 glass tube 100 g resin, 1% TBPB
Time from 40 °C to peak	80 - 120 seconds	
Exothermic temperature (peak)	225 - 255 °C	

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** February 2021

**Physical characteristics of cured nonreinforced base resin:**

Property	Range	Method / According to standard
Density, 20 °C	1.21 - 1.23 kg/L	ISO 1183
Tensile strength	35 - 50 MPa	ISO R 527
Elongation at break	1.0 - 2.0%	ISO R 527
Flexural strength	90 - 100 MPa	ISO 178
E - modulus in tension	3400 - 3600 MPa	ISO R 527
Impact resistance	8 - 12 kJ/m <sup>2</sup>	ISO 179
Heat distortion temperature	130 - 140 °C	ISO 75 A
Glass transition temperature	180 - 200 °C	ISO 537

**Handling and safety precautions:**

Colpoly 7795 is flammable liquid and should be kept away from naked flames. For further details, please see the relevant Safety Data Sheet.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** February 2021