

COLPOLY LPA 2600

Saturated Polyester Resin

Description:

Saturated polyester resin based on adipic acid and mixed glycols, dissolved in styrene.

Application:

LP-additive.

Features and benefits:

- » Used together with other LP-additives in SMC and BMC formulations.
- » High surface quality.

Physical characteristics of the liquid resin:

Property	Range	Method / According to standard
Appearance	Clear - slightly hazy	
Acid value	5 - 10 mg KOH/g	MH1051 / ISO 2114
Styrene content	29 - 31%	MH2034
Viscosity, 23 °C	1400 - 1600 mPa·s	MH1009 / ISO 3219
Colour	max. 200 APHA	MH1125 / ISO 6271
Flash point	34 °C	DIN 51 755
Shelf life at 25 °C in darkness	4 months	

Handling and safety precautions:

Colpoly LPA 2600 is flammable liquid and should be kept away from naked flames. For further details, please see the relevant Safety Data Sheet.

Note: The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

Edition: July 2023