

## COLPOLY LPA 2600

### Saturated Polyester Resin

**Description:**

Saturated polyester resin based on adipic acid and mixed glycols, dissolved in styrene.

**Application:**

LP-additive.

**Features and benefits:**

- » Used together with other LP-additives in SMC and BMC formulations.
- » High surface quality.

**Physical characteristics of the liquid resin:**

| Property                        | Range                 | Method / According to standard |
|---------------------------------|-----------------------|--------------------------------|
| Appearance                      | Clear - slightly hazy |                                |
| Acid value                      | 5 - 10 mg KOH/g       | MH1051 / ISO 2114              |
| Styrene content                 | 29 - 31%              | MH2034                         |
| Viscosity, 23 °C                | 1400 - 1600 mPa·s     | MH1009 / ISO 3219              |
| Colour                          | max. 200 APHA         | MH1125 / ISO 6271              |
| Flash point                     | 34 °C                 | DIN 51 755                     |
| Shelf life at 25 °C in darkness | 4 months              |                                |

**Handling and safety precautions:**

Colpoly LPA 2600 is flammable liquid and should be kept away from naked flames. For further details, please see the relevant Safety Data Sheet.

**Note:** The information contained herein is provided in good faith and is to the best of our knowledge accurate, but we assume no liability for its accuracy or completeness. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety information please refer to the current Material Safety Data Sheet.

**Edition:** February 2021